

## TRANSPOL

### MODE D'EMPLOI

Lavage 40°C max

	Température .....	<b>150 °C</b>
	Temps de pose.....	<b>15 secondes</b>
	Pression.....	<b>moyenne (2-3 bars)</b>
	Démoulage.....	<b>à froid</b>

Ces valeurs sont données à titre indicatif : effectuer toujours des tests avant de lancer une production.

Le Transpol «classique» n'adhère pas sur les fibres nylon fortement imperméabilisées .

### CONSEILS

- Ne pas repasser directement (vêtement à l'envers)
- Tendre les vêtements pour éviter les faux plis et les surépaisseurs (boutons, bas de maillots, coutures de manches, cols, autres logos...)
- Enfiler les vêtements dans les jeannettes
- Fibre nouvelle : procéder à des essais ou nous consulter
- Nettoyage à sec : non recommandé

# monblason

Heat transfer solutions / Since 1906

## TRANSPOL

### INSTRUCTIONS

Washable up to 40°C

	Temperature .....	<b>150 °C</b>
	Pressing time.....	<b>15 seconds</b>
	Pressure.....	<b>middle (2-3 bars)</b>
	Peeling.....	<b>cold</b>

These settings are given for guidance : always give a try before strating a production.  
Standard TRANSPOL does not stick on strongly waterproof nylon.

### ADVICES

- Cannot be ironed directly (ironed the garment inside out)
- Correctly stretch the garment to avoid folds and thicknesses (mind buttons, tee-shirt edges, sleeve sewings, neckband, other logos...)
- Slip on the garment using the press table
- Unknown fiber : do a test or contact us
- Dry cleaning is not recommended

[www.monblason.com](http://www.monblason.com)